

Fluorinar™ Kynar® PVDF Filament

3D printing is an exciting additive manufacturing method. However, available filament materials for engineers and chemists lack the corrosion resistance required for many industrial applications. With Fluorinar™ Kynar® PVDF filament reality has changed. Advantages of Fluorinar™ filament include:

- » Rapid part production in small quantities
- » Production of solid stock for CNC machining when tight part tolerances are required
- » Easy to print filament settings can be achieved on most consumer-grade printers
- » Wide melt window means no outgassing during part production
- » Final parts are corrosion resistant and can be exposed to a wide range of chemistries
- » Withstand UV and ionizing radiation without mechanical compromise

Fluorinar filament is made from 100% PVDF without processing aids, stabilizers, colorant or fillers.

Fluorinar™ Kynar® PVDF Print Settings

Print Quality	Filament Material	Color	Raft	Extrusion Temp (C)	Bed Temp (C)	Print Speed (mm/sec)	Layer Height (mm)
Standard	Fluorinar™	Natural	Yes	240 - 250	100	50	0.25
High	Fluorinar™	Natural	Yes	240 - 250	100	30	0.14

Fluorinar™ Kynar® PVDF Filament Properties

Part Number	Materials	Color	Filament Diameter (mm)	Diameter Tolerance (mm)	Filament Spool Weight (g)	USP Class VI
NPF175N	Kynar PVDF	Natural	1.75	+/- 0.05	500	Yes
NPF285N	Kynar PVDF	Natural	2.85	+/- 0.05	500	Yes

Kynar® PVDF Material Properties

Physical Properties	Standards	Units	Results
Refractive Index	ASTM D542	-	1.42
Specific Gravity	ASTM D742	-	1.77 - 1.80
Water Absorption	ASTM D570	%	0.03 - 0.05
Mechanical Properties			
Flexural Strength at 5% Strain	ASTM D790	psi	3,000 - 5,000
Flexural Modulus	ASTM D790	psi	150,000 - 180,000
Tensile Yield Elongation	ASTM D638	%	5 - 15
Tensile Yield Strength	ASTM D638	psi	4,500 - 6,000
Tensile Break Elongation	ASTM D638	%	30 - 200
Tensile Break Strength	ASTM D638	psi	4,000 - 7,000
Tensile Modulus	ASTM D638	psi	150,000 - 220,000
Deflection Temperature	ASTM D648 at 66 psi	°F	140 - 167
Hardness	ASTM D2240	Shore D	70 - 75
Thermal Properties			
Melting Temperature	ASTM D3418	°F	311 - 320
Thermal Conductivity	ASTM D433	BTU-in/hr.ft² F	1.0 - 1.25
Electrical Properties			
Dielectric Strength	ASTM D149	KV/mil	1.3 - 1.6
Volume Resistivity	ASTM D257	ohm-cm	2 x 10 ¹⁴
Flame and Smoke Properties			
Burning Rate	UL/Bulletin 94	-	V - O
Limiting Oxygen Index	ASTM D2868	% O ₂	43/75

Kynar® PVDF Chemical Resistance

Chemical	Concentration	Maximum Temperature °F
Acetic Acid	50% in water	200
Acetone		Not Recommended
Brine		275
Bromine, liquid		150
Chlorine, liquid		175
Chromic Acid	Up to 40% in water	175
Hydrochloric Acid	Up to "concentrated"	275
Hydrofluoric Acid	41 - 100%	200
Nitric Acid	11 - 70% in water	150
Phosphoric Acid	Less than 85% in water	275
Sulfuric Acid	Up to 60% in water	250



Fluorinar™ Kynar® PVDF Filament is packaged in the USA by Nile Polymers, Inc.
Contact us at (801) 203-3756 or sales@nilepolymers.com

The statements, technical information and recommendations are believed to be accurate. Since the conditions and methods of use of the product and of the information referred to are beyond our control, Nile Polymers expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization.